

TECHNICAL DATA SHEET FIBERLOGY MATTE PLA

Fiberlogy MATTE PLA

MANUFACTURER:

DESCRIPTION:

TRADE NAME:

Fiberlab S.A., Brzezie 387, 32-014 Brzezie, Poland

MATTE PLA filament designed for printing in FFF/FDM technology, available in different colors, wound on a spool or as a refill, vacuum-packed in a plastic bag, placed in a cardboard box.

TECHNICAL INFORMATION:

Diameter: Diameter Tolerance: Avg Roundness: Net Weight: Print Temperature: Bed Temperature: 1.75 mm +/- 0.02 mm + 0.01 mm 0.85 kg 200°C - 230°C 60°C



Physical Properties	Test Method	Unit	Typical Value
Specific Density	ASTM D792	g/cm ³	1.24
Mechanical Properties	Test Method	Unit	Typical Value
Tensile Strength @ Yield	ASTM D882	MPa	41
Elongation @ Yield	ASTM D882	%	4
Flexular Strength	ASTM D790	MPa	48
Thermal Properties	Test Method	Unit	Typical Value
Heat Distortion Temperature @ 0.45 MPa	ASTM E2092	°C	55
Glass Transition Temperature Tg	ASTM D3418	°C	55 - 60
Melting Temperature Tm	ASTM D3418	0°	145 - 160

The information set forth herein has been gathered from standard reference materials and/or supplier test data. To the best knowledge and belief of Fiberlab S.A. they are accurate and reliable. Information is offered only for your consideration, investigation and verification. Fiberlab S.A. makes no warranties, expressed or implied, with respect to the use of such information or the use of the specific material identified herein combination with any other material or process, and assumes no responsibility therefore.

Last update: June 25, 2025